



ACID#8

DRIVING SURFACE PERFECTION

TECHNICAL DATA SHEET

Version: 1.0

Acid Etch Primer

TECHNICAL DATA SHEET & PROCESS GUIDE

ACID #8 is a 1K ready to use etch primer available in 1 litre cans. It is used for priming bare metal surfaces, this promotes adhesion of paint and prevents steel from rusting.

ACID #8 is chromate free. Typical applications are over rub through areas prior to painting, on new bare metal panels or over bare seams before sealant is applied.

PROPERTIES

ACID#8 can be applied to the following surfaces:

- Bare metal such as steel, zinc galvanised and aluminium
- Can be air dried or low baked

Available Colours

- Grey

TECHNICAL DATA



Substrates

- Aluminium
- Mild Steel
- Galvanised

Viscosity

34 - 38 seconds BS4

Specific gravity g/cm³

1.03

APPLICATION GUIDE



Tools Required

- Degreaser
- HVLV Gravity Gun
- Abrasives
- Painters Overalls



Substrate Preparation

To achieve best results, good preparation is essential. Degrease with U-POL Precleaner (S2000, S2001 or S2002). Abrade the surface:

Bare Metal (mild steel): abrade with P180 - P240

Aluminium and zinc coated steel: P180 - P240

Before applying primer, clean lightly once more with SYSTEM 20 Degreasers and dry thoroughly.



Viscosity Poise

34 - 38 seconds BS4

Working Pot-Life @ 20°C

n/a

TECHNICAL DATA SHEET & PROCESS GUIDE



Compliant HVLP Gravity Gun

Gun tip size 1.2- 1.3mm

Air Pressure at the gun 1.8 - 2.0 bar

The product can be thinned up to 5% with alcohol, e.g. IMS/Butanol.

Equipment can be cleaned with an alcohol based thinner.



Coats

Build / microns approx 20 - 30

1 - 2 coats



Flash-off @ 20°C

Between coats 3 - 5 mins



Drying Times

overcoat time @ 20°C 10 - 20 mins



Over Painting

ACID#8 1K Acid Etch Primer may be overpainted with most paints. If the repair requires additional build primer filler should be used before topcoat is applied.

STORAGE & VOC INFORMATION



Shelf Life

2 years from date of manufacture in sealed original containers.

Recommended Storage Temperature 5°C - 25°C

Equipment Cleaning Equipment can be cleaned with an alcohol based thinner.

VOC Information



The EU limit for this product (product category: IIBc) in ready to use form is 780g/litre.

The VOC content of this product in ready to use form is 717g/litre.

Order Code	Format	Colour
ACID/1	1L Tin	Grey Primer



ACID#8

DRIVING SURFACE PERFECTION

TECHNICAL DATA SHEET

Version: 1.0

Acid Etch Primer

TECHNICAL DATA SHEET & PROCESS GUIDE

IMPORTANT: FOR PROFESSIONAL USE ONLY. Read full instructions before use.

This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the safety data sheet for full handling instructions and personal protection information. U-POL disclaims any liability where the user does not wear the recommended personal protective equipment. The above data is for information only and may change without prior notice. It is the Buyers responsibility to ensure the suitability of the products for their own use and check the information is up to date. The recommendation of use of our products and application in our technical data sheets are based on our knowledge and experience. These data sheets are available via your local stockist or via the U-POL website at WWW.U-POL.COM. U-POL is not responsible for the results obtained by others over whose methods we have no control and thereof U-POL is not liable for consequential or incidental damages including loss of profits.

U-POL AUSTRALIA PTY Ltd

PO BOX 375

Springwood NSW 2777

WWW.U-POL.COM

Contact Australia

T: +61 2 4731 2655

F: +61 2 4731 2611
sales@u-pol.com.au

U-POL NEW ZEALAND Ltd

T: +64 27 630 3691

F: +61 2 4731 2611
sales@u-pol.com

Technical

T: +44 (0)1933 230 310

F: +44 (0)1933 425 797
technicaldepartment@u-pol.com
